



ACRIC EZ CLEAR-Q

TYPE	Super quick drying polyurethane coating of catalytic reaction type acrylic polyol and non-yellowing hardener
USES	Fast drying high quality clearcoat finish for refinishing of cars (touch-up & overall coating)
CHARACTERISTICS	<ol style="list-style-type: none">1. Outstanding film appearance2. Extremely durable3. High gloss retention4. Very fast drying-shorter process time
APPLICATION DATA	
COLOUR	Clear
APPLICATION METHOD	Airspray
THINNER	Acric EZ Thinner
THINNING RATIO	20 – 40% (by weight)
MIXING RATIO	Base : Hardener = 2 : 1 (by weight)
POT LIFE	3 hours at 30°C
SPREADING RATE	8.0 – 10.00 m ² /Ltr/Coat
DRY FILM THICKNESS	30 – 35 microns/Coat
DRYING TIME	Touch Dry : 3 minutes at 30°C Polishable : 3 hours at 30°C Full Cure : 24 hours at 30°C
GENERAL INFORMATION	
PACKING SIZE	1 Litre & 4 Litres
RECOMMENDED COATINGS	Acric EZ Basecoat
SHELF LIFE	I.A.W. ISO Control Of Finished Product Shelf Life Procedures, the shelf life (Existing) is 24 months from date of shipment. <ul style="list-style-type: none">• Spreading rate changes depending on application technique, weather, wastage and surface conditions.



ACRIC EZ 2K HARDENER

Type	Non-yellowing type isocyanate-based hardener, which provides good durability to coated film (base on isocyanate)
Uses	As standard hardener of Acric EZ 2K Clear Q and Acric EZ Base coat (solid, metallic & pearl)
Characteristics	1) Extremely durable and high gloss 2) Good adhesion for EZ base coat

APPLICATION DATA

Colour	Transparent																				
Application Method	Airspray																				
Thinner	Acric EZ Thinner																				
Drying Time	Depending on mixing paint (base coat or clear)																				
Mixing Ratio	Base/hardener/thinner for each coat: <table border="1"><thead><tr><th></th><th>Base</th><th>Hardener</th><th>Thinner</th></tr></thead><tbody><tr><td>EZ Color Base: Solid</td><td>100</td><td>20</td><td>50-100</td></tr><tr><td> Metallic</td><td>100</td><td>20</td><td>100-120</td></tr><tr><td> Pearl</td><td>100</td><td>20</td><td>100-120</td></tr><tr><td>EZ 2K Clear Q Base</td><td>100</td><td>50</td><td>20-40</td></tr></tbody></table>		Base	Hardener	Thinner	EZ Color Base: Solid	100	20	50-100	Metallic	100	20	100-120	Pearl	100	20	100-120	EZ 2K Clear Q Base	100	50	20-40
	Base	Hardener	Thinner																		
EZ Color Base: Solid	100	20	50-100																		
Metallic	100	20	100-120																		
Pearl	100	20	100-120																		
EZ 2K Clear Q Base	100	50	20-40																		

GENERAL INFORMATION

Specific Gravity	0.92 – 0.96
Packing Size	0.5 Litre, 1 Litre & 4 Litres
Flash Point	4°C
Recommended Undercoat	Acric EZ 2K Clear Q and EZ Basecoat (Solid/Metallic/Pearl)